

Technical Data Sheet

Hostacom EKC 330N C6 NAT



Polypropylene Compounds

Product Description

Hostacom EKC 330N C6 NATURAL is a 15% talc filled, impact modified grade for interior applications with excellent stiffness/impact balance, good flowability properties and excellent scratch resistance. The grade is available in color-matched, pellet form.

Regulatory Status

For regulatory compliance information, see Hostacom EKC 330N C6 NAT [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Asia-Pacific
Application	Automotive Parts; Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Processability; High Impact Resistance; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	14	g/10 min	ISO 1133-1
Density, (23 °C)	1.02	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1600	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	15	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	30	kJ/m ²	ISO 179-1/1eA

Notes

These are typical property values not to be construed as specification limits.