

## Technical Data Sheet

### Hostacom EP3307 G12771



Polypropylene Compounds

#### Product Description

Hostacom EP3307 G12771 is an unfilled PP copolymer, with high impact resistance and good UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in G12771 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

|                   |                        |
|-------------------|------------------------|
| Application       | Interior Trims         |
| Market            | Automotive             |
| Processing Method | Injection Molding      |
| Attribute         | High Impact Resistance |

| Typical Properties                                        | Nominal Value | Units             | Test Method   |
|-----------------------------------------------------------|---------------|-------------------|---------------|
| <b>Physical</b>                                           |               |                   |               |
| Melt Flow Rate, (230 °C/2.16 kg)                          | 16            | g/10 min          | ISO 1133-1    |
| Density, (23 °C)                                          | 0.90          | g/cm <sup>3</sup> | ISO 1183-1/A  |
| <b>Mechanical</b>                                         |               |                   |               |
| Flexural Modulus, (23 °C, Tech. A)                        | 1100          | MPa               | ISO 178/A1    |
| Tensile Stress at Yield, (23 °C)                          | 19            | MPa               | ISO 527-1, -2 |
| <b>Impact</b>                                             |               |                   |               |
| Charpy Impact Strength - Notched                          |               |                   |               |
| (23 °C)                                                   | 45            | kJ/m <sup>2</sup> | ISO 179-1/1eA |
| (-40 °C)                                                  | 4             | kJ/m <sup>2</sup> | ISO 179-1/1eA |
| Notched Izod Impact Strength                              |               |                   |               |
| (23 °C)                                                   | 40            | kJ/m <sup>2</sup> | ISO 180/1A    |
| (-40 °C)                                                  | 5             | kJ/m <sup>2</sup> | ISO 180/1A    |
| <b>Thermal</b>                                            |               |                   |               |
| Deflection Temperature Under Load, (0.45 MPa, Unannealed) | 80            | °C                | ISO 75B-1, -2 |