(+) 188 1699 6168 hongrunplastics.com

## **Technical Data Sheet**

# Hostacom EP380X PG05

Polypropylene Compounds

# lyondellbasell

### **Product Description**

*Hostacom* EP380X PG05 is an unfilled polypropylene copolymer, with high melt flow rate offering a good impact/stiffness balance. Product is available as a customized color matched, pellet form. This grade is delivered in PG05 color version.

### **Regulatory Status**

For regulatory compliance information, see *Hostacom* EP380X PG05 <u>Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS)</u>.

Status Commercial: Active

Availability Asia-Pacific

**Application** Interior Automotive Applications

Market Automotive

Processing Method Injection Molding

Attribute Good Impact Resistance; High Flow; UV Resistant

|   | Nominal |          |               |
|---|---------|----------|---------------|
| Typical Properties  | Value   | Units    | Test Method   |
| Physical  |         |          |               |
| Melt Flow Rate, (230 °C/2.16 kg)                          | 27      | g/10 min | ISO 1133-1    |
| Density, (23 °C, Method A)                                | 0.90    | g/cm³    | ISO 1183-1    |
| Mechanical  |         |          |               |
| Flexural Modulus  | 1400    | MPa      | ISO 178       |
| Tensile Stress at Yield                                   | 23.5    | MPa      | ISO 527-1, -2 |
| Impact  |         |          |               |
| Notched Izod Impact Strength, (23 °C)                     | 9       | kJ/m²    | ISO 180/1A    |
| Thermal   |         |          |               |
| Deflection Temperature Under Load, (0.45 MPa, Unannealed) | 85      | °C       | ISO 75B-1, -2 |

### **Notes**

These are typical property values not to be construed as specification limits.