

Technical Data Sheet

Hostacom EYC 136N C12A24



Polypropylene Compounds

Product Description

Hostacom EYC 136N C12A24 is a 13% talc filled PP copolymer, with excellent flowability, high stiffness, high dimensional stability and excellent scratch resistance. It has been designed using the latest advancements in resin synthesis and compounding technology. This grade is delivered in customer customized colors. This grade is delivered in C12A24 onyx black color version

This product is also available in other colors, new colors can be developed depending on customer requirements.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Dimensional Stability; High Stiffness; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	22	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2000	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	23	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	6	kJ/m ²	ISO 179-1/1eA
(-40 °C)	2	kJ/m ²	ISO 179-1/1eA
Notched Izod Impact Strength			
(23 °C)	5	kJ/m ²	ISO 180/1A
(-40 °C)	2.5	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	105	°C	ISO 75B-1, -2