(+) 188 1699 6168 hongrunplastics.com

## **Technical Data Sheet**

# Hostacom EYC 319N C12699

Polypropylene Compounds

## **Product Description**

*Hostacom* EYC 319N C12699 is a 14% talc filled PP copolymer, with high flowability and good impact/stiffness balance. The product is available in different color matched, pellet form. This grade is delivered in C12699 color version.

#### **Regulatory Status**

For regulatory compliance information, see *Hostacom* EYC 319N C12699 <u>Product Stewardship Bulletin (PSB)</u> and Safety Data Sheet (SDS).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status Commercial: Active

**Availability** Europe

Application Interior Trims
Market Automotive

Processing Method Injection Molding

Attribute Good Processability; High Flow; Low Density; UV Resistant

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	29	g/10 min	ISO 1133-1
Density, (23 °C)	0.99	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1600	MPa	ISO 178/A1
Tensile Strength, (23 °C)	20	MPa	ISO 527-1, -2
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	100	°C	ISO 75B-1, -2

#### **Notes**

These are typical property values not to be construed as specification limits.

