

Technical Data Sheet

Hostacom SP 98/F/94 1740



Polypropylene Compounds

Product Description

Hostacom SP 98/F/94 1740 is a 30% talc filled PP copolymer, with medium melt flow, high stiffness and good impact resistance. Product is available as a customized color matched, pellet form. This grade is delivered in 1740 color version.

Regulatory Status

For regulatory compliance information, see Hostacom SP 98/F/94 1740 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Europe
Application	Automotive Parts; Exterior Trim
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	7	g/10 min	ISO 1133-1
Density, (23 °C)	1.15	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2000	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	22	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C)	50	%	ISO 527-1, -2

Notes

These are typical property values not to be construed as specification limits.