

Technical Data Sheet

Hostacom TKC 471N NA NATURAL



Polypropylene Compounds

Product Description

Hostacom TKC 471N NA NATURAL medium melt flow, 1,650 MPa flexural modulus, mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent balance of processability, rigidity, impact and scratch and mar resistance. It is typically used for molded-in color interior applications.

Application	Automotive Parts; Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance; Good Processability; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C)	0.96	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1650	MPa	ISO 178
Tensile Stress at Yield	20	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	40	kJ/m ²	ISO 180
(-40 °C)	4	kJ/m ²	ISO 180
Thermal			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	53	°C	ISO 75A-1, -2
Additional Information			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			