

Technical Data Sheet

Hostacom TRC 160N HF LS NATURAL



Polypropylene Compounds

Product Description

Hostacom TRC 160N HF LS NATURAL is a 16% mineral filled, polypropylene copolymer for injection molding. It combines excellent stiffness/impact balance, good scratch resistance, low odor and excellent flowability properties with good dimensional stability. It is typically used for molding of automotive interior trim parts.

Regulatory Status

For regulatory compliance information, see Hostacom TRC 160N HF LS NATURAL [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Automotive Parts; Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Moldability; Good Stiffness; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	32	g/10 min	ISO 1133-1
Density, (23 °C)	1.00	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1750	MPa	ISO 178
Tensile Stress at Yield	20	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	50	kJ/m ²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	98	°C	ISO 75B-1, -2
Additional Information			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			

Notes

These are typical property values not to be construed as specification limits.