

Technical Data Sheet

Hostacom TRC 2367N C11675



Polypropylene Compounds

Product Description

Hostacom TRC 2367N C11675 is a talc filled PP copolymer, with good flowability, excellent impact/stiffness balance and high scratch resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C11675 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Instrument Panels
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ISO 1133-1
Density, (23 °C)	1.04	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2000	MPa	ISO 178/A1
Impact			
Notched Izod Impact Strength			
(23 °C)	40	kJ/m ²	ISO 180/1A
(-30 °C)	3.5	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	106	°C	ISO 75B-1, -2