

Technical Data Sheet

Hostacom TRC 352N R C11306



Polypropylene Compounds

Product Description

Hostacom TRC 352N R is a 20% talc filled PP copolymer, with excellent blooming resistance at elevated temperatures, very good impact/stiffness balance, very good processability, very good scratch resistance and good surface appearance. Please contact LyondellBasell for shrinkage recommendations. This grade is delivered in Color C11306.

Regulatory Status

For regulatory compliance information, see Hostacom TRC 352N R C11306 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Europe
Application	Automotive Parts; Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Moldability; Non Blooming; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	19	g/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1900	MPa	ISO 178/A1
Impact			
Charpy Impact Strength - Notched			
(23 °C)	24	kJ/m ²	ISO 179-1/1eA
(-30 °C)	3	kJ/m ²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	No Break		ISO 179-1/1eU

Notes

These are typical property values not to be construed as specification limits.