

Technical Data Sheet

Hostacom TRC 483N NA KX8A DKSLTE



Polypropylene Compounds

Product Description

Hostacom TRC 483N NA KX8A DKSLTE is a high flow, mineral-filled UV stabilized thermoplastic elastomeric olefin (TEO) resin with excellent balance of processability, rigidity, impact and scratch/mar resistance that is typically used for interior trim and door panel applications.

Application	Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Excellent Processability; High Impact Resistance; High Rigidity; Scratch Resistant; UV Stabilized

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C)	1.03	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C)	1600	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	17	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	60	kJ/m ²	ISO 179
(-40 °C)	4.3	kJ/m ²	ISO 179
Thermal			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	48	°C	ISO 75A-1, -2
Additional Information			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			