

## Technical Data Sheet

### Hostacom X 4305 HL86 C11336



Polypropylene Compounds

#### Product Description

Hostacom X 4305 HL86 C11336 is a 20% talc filled PP copolymer, with good stiffness, good toughness and superior UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C11336 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

|                   |                                                                  |
|-------------------|------------------------------------------------------------------|
| Application       | Interior Trims                                                   |
| Market            | Automotive                                                       |
| Processing Method | Injection Molding                                                |
| Attribute         | Good Flow; Good Impact Resistance; Medium Rigidity; UV Resistant |

| Typical Properties                 | Nominal Value | Units             | Test Method  |
|------------------------------------|---------------|-------------------|--------------|
| <b>Physical</b>                    |               |                   |              |
| Melt Flow Rate, (230 °C/2.16 kg)   | 16            | g/10 min          | ISO 1133-1   |
| Density, (23 °C)                   | 1.04          | g/cm <sup>3</sup> | ISO 1183-1/A |
| <b>Mechanical</b>                  |               |                   |              |
| Flexural Modulus, (23 °C, Tech. A) | 2300          | MPa               | ISO 178/A1   |