

Technical Data Sheet

Hostacom X 4323/3 S63 305514



Polypropylene Compounds

Product Description

Hostacom X 4323/3 S63 305514 is a 20% talc filled PP copolymer, with low odour, low flowability and low emissions. Product is available as a customized color matched, pellet form. This grade is delivered in 305514 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	7	g/10 min	ISO 1133-1
Density, (23 °C)	1.06	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2200	MPa	ISO 178/A1
Impact			
Charpy Impact Strength - Notched, (23 °C)	7.2	kJ/m ²	ISO 179-1/1eA