

Technical Data Sheet

Hostacom X M2 U34 102942



Polypropylene Compounds

Product Description

Hostacom X M2 U34 102942 is a 22% talc filled PP homopolymer, with high flowability, high stiffness, low odour and high thermal resistance. Product is available as non color matched, black, pellet form. This grade is delivered in 102942 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Automotive Parts
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	10	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/2.16 kg)	12	cm ³ /10 min	ISO 1133-1
Density, (23 °C)	1.06	g/cm ³	ISO 1183-1/A
Mechanical			
Tensile Modulus, (23 °C)	2900	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	35	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	3	kJ/m ²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	40	kJ/m ²	ISO 179-1/1eU
Thermal			
Vicat Softening Temperature, (B50)	95	°C	ISO 306
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	70	°C	ISO 75A-1, -2