

Technical Data Sheet

Hostacom X M3 T16 100000



Polypropylene Compounds

Product Description

Hostacom X M3 T16 100000 is a 30% talc filled PP copolymer, with medium melt flow rate and good impact/stiffness balance. The product is available in different color matched, pellet form.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	7	g/10 min	ISO 1133-1
Density, (23 °C)	1.14	g/cm ³	ISO 1183-1/A
Mechanical			
Tensile Stress at Yield, (23 °C)	24	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C)	5	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	6	kJ/m ²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	40	kJ/m ²	ISO 179-1/1eU
Thermal			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	65	°C	ISO 75A-1, -2