

Technical Data Sheet

Hostalen PP H2464



Polypropylene, Impact Copolymer

Product Description

Hostalen PP H2464 is a natural polypropylene copolymer with an good mechanical properties balance. The product is typically used by customers in the application of solid and structured wall pipes for underground drainage and sewage systems. The product can enable customers to reach medium pipe ring stiffness and good impact strength for installations at room temperature and in particular at sub-zero temperatures. For further details about the suitable applications for this material please contact LyondellBasell.

Regulatory Status

For regulatory compliance information, see Hostalen PP H2464 [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical and pharmaceutical applications.

This grade is supported for use in drinking water applications.

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand; Europe
Application	Soil & Waste Pipe
Market	Pipe
Processing Method	Pipe
Attribute	Block Copolymer

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate			
(230 °C/2.16 kg)	0.3	g/10 min	ISO 1133-1
(230 °C/5.0 kg)	1.3	g/10 min	ISO 1133-1
(190 °C/5.0 kg)	0.5	g/10 min	ISO 1133-1
Density	0.90	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus, (23 °C)	1350	MPa	ISO 527-1, -2
Tensile Stress at Yield	28	MPa	ISO 527-1, -2
Tensile Strain at Yield	13	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	55	kJ/m ²	ISO 179
(0 °C)	34	kJ/m ²	ISO 179
(-20 °C)	10	kJ/m ²	ISO 179
Thermal			
Oxidation Induction Time, (200 °C)	30	min	ISO 11357-6

Notes

These are typical property values not to be construed as specification limits.