(+) 188 1699 6168 hongrunplastics.com



Hostalen PP XN125-P

Polypropylene, Random Copolymer

Product Description

Hostalen PP XN125-P is a natural colored polypropylene random copolymer.

The product Hostalen PP XN125-P has been classified by ISO9080 and according to ISO12162 as PP125.

The regression curves of *Hostalen PP XN125-P* are above the reference lines of PP-RCT mentioned in DIN8077, DIN 8078 and EN ISO15874 standards for piping applications under pressure.

For further details about the suitable applications for this material please contact LyondellBasell. For regulatory information please refer to *Hostalen PP XN125-P Product Stewardship Bulletin (PSB)*.

Hostalen PP XN125-P is not intended for medical and pharmaceutical applications.

Product Characteristics

Status Commercial: Active

Test Method used ISO

Availability Europe

Processing Methods Extrusion Pipe Sheet and Semi Finished Products

Features Antioxidant, Random Copolymer, Good Organoleptic

Properties

Typical Customer Applications Industrial, Plumbing, Heating & Cooling

| Typical Properties | Method | Value | Unit |
|---------------------------------------|---------------|-------|----------|
| Physical | | | |
| Melt flow rate (MFR) | ISO 1133 | | |
| (190°C/5.0kg g/10 min) | | 0.4 | g/10 min |
| (230 °C/5.0 kg g/10 min) | | 1.1 | g/10 min |
| (230 °C/ 2.16 kg g/10 min) | | 0.2 | g/10 min |
| Mechanical | | | |
| Tensile Strain at Yield | ISO 527-1, -2 | 12 | % |
| Tensile stress at yield | ISO 527 | 26 | MPa |
| Tensile modulus | ISO 527 | 850 | MPa |
| MRS classification | ISO 9080 | 12.5 | MPa |
| Impact | | | |
| Charpy notched impact strength (0 °C) | ISO 179 | 8 | kJ/m² |
| Thermal | | | |
| Melting temperature | DSC | 136 | °C |
| | | | |

Additional Properties

Processing: the recommended conditions will depend on the type of equipment used by the material transformer and on the size and wall thickness of the produced pipes.

Recommended melt temperatures: 230-240°C

Recommended injection moulding temperatures: 230-280°C

Recommended cooling water temperature in extruder calibration area: 35-40°C