

Technical Data Sheet
Lucent PP GPP-320
Polypropylene
Engineering Plastics



Product Description

20% Glass Fiber Reinforced, Chemically Coupled, Impact Modified Polypropylene

Melt Flow Adjustable for Application

Colors Available

Add "U" for UV Stabilized

Add "H" for Heat Stabilized

General

Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Additive	• Impact Modifier
Features	• Chemically Coupled • Impact Modified
Appearance	• Colors Available

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04 g/cm ³	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	5.0E-3 in/in	0.50 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	7700 psi	53.1 MPa	ASTM D638
Tensile Elongation (Break)	5.0 %	5.0 %	ASTM D638
Flexural Modulus	375000 psi	2590 MPa	ASTM D790
Flexural Strength	10000 psi	68.9 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 in (3.18 mm))	3.0 ft-lb/in	160 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed	255 °F	124 °C	

Notes

These are typical property values not to be construed as specification limits.