

Technical Data Sheet

Matrixx 14N6022

Polypropylene
LyondellBasell Industries
Engineering Plastics

General		
Material Status	• Commercial: Active	
Availability	• North America	
Additive	• Flame Retardant	
Features	• Flame Retardant	• Low Blooming
Forms	• Pellets	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.990	0.988 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	18 g/10 min	18 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	3500 psi	24.1 MPa	ASTM D638
Flexural Modulus	175000 psi	1210 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	2.0 ft·lb/in	110 J/m	ASTM D256
Gardner Impact	170 in·lb	19.2 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	190 °F	87.8 °C	ASTM D648
RTI Elec	149 °F	65.0 °C	UL 746B
RTI Imp	149 °F	65.0 °C	UL 746B
RTI Str	149 °F	65.0 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	V-0	V-0	UL 94

Additional Information			
The value listed as Mold Shrinkage, ASTM D955, was tested in accordance with Matrixx test methods.			

Notes

These are typical property values not to be construed as specification limits.