

## Technical Data Sheet

### Moplen EP249R



Polypropylene, Impact Copolymer

#### Product Description

Moplen EP249R is a heterophasic copolymer with medium flow in injection molding. This grade is nucleated and characterized by a low temperature impact resistance.

Moplen EP249R is typically used by customers in crates, housewares and opaque containers.

#### Regulatory Status

For regulatory compliance information, see Moplen EP249R [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical and pharmaceutical applications.

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Crates; Housewares; Opaque Containers; Sports, Leisure & Toys
Market	Consumer Products; Rigid Packaging
Processing Method	Injection Molding
Attribute	Good Flow; Impact Copolymer; Low Temperature Impact Resistance; Nucleated

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	25	g/10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Tensile Modulus	950	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	20	kJ/m <sup>2</sup>	ISO 179
(0 °C, Type 1, Edgewise, Notch A)	10	kJ/m <sup>2</sup>	ISO 179
(-20 °C, Type 1, Edgewise, Notch A)	8	kJ/m <sup>2</sup>	ISO 179

#### Notes

These are typical property values not to be construed as specification limits.