



Moplen EP300K

Polypropylene, Impact Copolymer

Product Description

Moplen EP300K is a low fluidity heterophasic copolymer, suitable for injection moulding applications.
The product exhibits very high impact even at low temperature combined with a good stiffness.

Moplen EP300K is typically used in houseware items and in crates.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	Europe, Africa-Middle East
Processing Methods	Extrusion Thermoforming, Injection Molding
Features	High Impact Resistance , Good Stiffness
Typical Customer Applications	Caps & Closures, Crates, Housewares

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.9	g/cm³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	4	g/10 min
Melt volume flow rate (230°C/2.16Kg)	ISO 1133	5.4	cm³/10min
Mechanical			
Tensile Modulus	ISO 527-1, -2	1200	MPa
Tensile Stress at Yield	ISO 527-1, -2	27	MPa
Tensile Strain at Break	ISO 527-1, -2	>50	%
Tensile Strain at Yield	ISO 527-1, -2	7	%
Impact			
Charpy unnotched impact strength	ISO 179		
(23 °C, Type 1, Edgewise)		No Break	kJ/m²
(0 °C, Type 1, Edgewise)		140	kJ/m²
(-20 °C, Type 1, Edgewise)		80.0	kJ/m²
Charpy notched impact strength	ISO 179		
(23 °C, Type 1, Edgewise, Notch A)		10.5	kJ/m²
(0 °C, Type 1, Edgewise, Notch A)		5.5	kJ/m²
(-20 °C, Type 1, Edgewise, Notch A)		4	kJ/m²
Hardness			
Ball indentation hardness (H 358/30)	ISO 2039-1	53	MPa
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	75	°C
Vicat softening temperature	ISO 306		
(A50 (50°C/h 10N))		150	°C
(B50 (50°C/h 50N))		71	°C

Notes

Typical properties; not to be construed as specifications.