



# Moplen HP422H

## Polypropylene, Homopolymer

#### **Product Description**

Moplen HP422H is a modified polypropylene homopolymer designed for the production of BOPP films at very high speed. BOPP films produced with HP422H feature good mechanical properties, excellent barrier against moisture, odours, oxygen, good transparency and gloss. Coextruded films made of Moplen HP422H are widely used in the food packaging industry. Moplen HP422H does not contain any slip or antistatic agents and it is Calcium Stearate free.

For regulatory information please refer to Moplen HP422H Product Stewardship Bulletin (PSB).

## **Product Characteristics**

Commercial: Active Status

**Test Method used** ISO ASTM

**Availability** Europe, Africa-Middle East

**Processing Methods** BOPP

Moisture Barrier, High Clarity, High Gloss, **Features** 

Homopolymer, Low to No Odor

**Typical Customer Applications** Barrier Film, BOPP, Film, Food Packaging Film

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.900	g/cm³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	2.0	g/10 min
Mechanical			
Tensile Modulus (1 mm/min)	ISO 527-1, -2	1450	MPa
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	34.0	MPa
Tensile Strain at Break (50 mm/min)	ISO 527-1, -2	410	%
Tensile Strain at Yield (50 mm/min)	ISO 527-1, -2	10	%
Hardness			
Shore hardness (Shore D)	ISO 868	70	
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	88.0	°C
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	152	°C

## **Additional Properties**

Typical Film Properties of monolayer film produced on T.M. Long equipment, a laboratory simultaneous film stretcher (7x7@150°C):

Haze, ASTM D 1003, 20  $\mu m \colon 0.50\%$ 

Tensile Tangent Modulus (0-1%), MA 18068, 5 mm/min, 20  $\mu$ m: 2400 MPa Stress at Break, MA 18068, 50 mm/min, 20  $\mu$ m: 116 MPa Elongation at Break, MA 18068, 50 mm/min, 20  $\mu$ m: 29%

Typical properties; not to be construed as specifications.