## (+) 188 1699 6168 hongrunplastics.com

### **Technical Data Sheet**

### Moplen QCP840P

Polypropylene, Impact Copolymer

# lyondellbasell

### **Product Description**

*Moplen* QCP840P is a 20% talc-filled circular polypropylene copolymer supplied in pellet form for injection moulding applications. The grade combines high stiffness, impact and flow. The grade is available in grey color.

#### Sustainability

Moplen QCP840P contains at least 75% of post-consumer material from pre-sorted municipal plastic packaging waste. Filtration level is 150  $\mu$ m. Volatiles according to ASTM D6980 @ 120 °C are < 0.2%. Based on CIELab values, the color indication is close to RAL 7043.

This product is not intended for highly regulated applications including food contact, potable water contact, medical and pharmaceutical applications.

Status Commercial: Active

**Availability** Europe

600 °C

ApplicationContainers; Crates; Furniture; PailsMarketConsumer Products; Rigid Packaging

Processing Method Injection Molding

Attribute General Purpose; Good Processability; High Rigidity; High Stiffness; Impact

Copolymer

No	minal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	12	g/10 min	ISO 1133-1
Density	1.050	g/cm³	ISO 1183-1
Bulk Density	0.680	g/cm³	ISO 60
Mechanical			
Flexural Modulus, (23 °C)	2100	MPa	ISO 178
Injection molded specimens prepared in accordance with ISO 1872-2.			
Tensile Modulus, (23 °C)	2250	MPa	ISO 527-1, -2
Injection molded specimens prepared in accordance with ISO 1872-2.			
Tensile Strength, (23 °C)	27	MPa	ISO 527-1, -2
Injection molded specimens prepared in accordance with ISO 1872-2.			
Tensile Strain at Break, (23 °C)	60	%	ISO 527-1, -2
Injection molded specimens prepared in accordance with ISO 1872-2.			
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	4.0	kJ/m²	ISO 179-1/1eA
Injection molded specimens prepared in accordance with ISO 1872-2.			
Additional Information			
Ash	20	wt %	ISO 3451-1