

# Moplen RP210G

## Polypropylene, Random Copolymer

#### **Product Description**

"Moplen" RP210G is a medium modified polypropylene random copolymer designed for blow moulding and sheet & film extrusion. It offers low density, stress cracking resistance and high chemical resistance. Main applications are extrusion of film for packaging & sheet for stationery folders and displays, the extrusion blow moulding of high gloss monolayer bottles, clear or pigmented, for the packaging of cosmetics, detergents, chemicals and food-stuffs. "Moplen" RP210G is suitable for food contact.

For regulatory information please refer to "Moplen" RP210G Product Stewardship Bulletin ( PSB ).

### **Product Characteristics**

**Status** Commercial: Active

Test Method used ISC

Availability Europe, Africa-Middle East

**Processing Methods** Double Bubble, Extrusion Blow Molding, Extrusion Pipe

Sheet and Semi Finished Products, Injection Blow

Molding

Features Good Chemical Resistance, Random Copolymer, Low

Density, High ESCR (Environmental Stress Cracking

Resistance), High Gloss

**Typical Customer Applications** Blow Moulding Applications, Bottles For Consumer

Goods, Double Bubble Shrink Film, Food Packaging Film,

Stationery Film, Thermoformed Food Containers

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.900	g/cm³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	1.8	g/10 min
Mechanical			
Tensile Modulus (1 mm/min)	ISO 527-1, -2	950	MPa
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	25.0	MPa
Tensile Strain at Yield (50 mm/min)	ISO 527-1, -2	14	%
Impact			
Charpy notched impact strength	ISO 179		
(23 °C, Type 1, Edgewise, Notch A)		6.00	kJ/m²
(0, Type 1, Edgewise, Notch A)		2.00	kJ/m²
Hardness			
Shore hardness (Shore D)	ISO 868	67	
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	70.0	°C
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	134	°C

### Notes

Typical properties; not to be construed as specifications.