

Technical Data Sheet

Polyfort POLYFORT FPP 1512E

Polypropylene
LyondellBasell Industries
Engineering Plastics

Product Description

POLYFORT® FPP 1512E is a 10% Talc-Filled, Low-Flow Polypropylene

General

Material Status	• Commercial: Active		
Availability	• North America		
Appearance	• Colors Available		
Processing Method	• Extrusion	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	0.83 g/10 min	0.83 g/10 min	ASTM D1238


Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	4920 psi	33.9 MPa	ASTM D638
Flexural Modulus - Secant ¹	276000 psi	1900 MPa	ASTM D790

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	237 °F	114 °C	ASTM D648

Technical Data Sheet

Polyfort POLYFORT FPP 1512E

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Moderate-Fast	Moderate-Fast

Injection Notes

Polypropylene is not hygroscopic and generally does not require drying. As a good practice and to avoid residual humidity from transport or storage conditions, we recommend drying the material.

Ensure good mold venting

Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

These are typical property values not to be construed as specification limits.