

Technical Data Sheet

Polyfort FPP1A15CCBKBLK



Polypropylene, Unspecified (PP, Unspecified)

Product Description

FPP1A15CC is a 15% Glass-Reinforced Chemically Coupled Polypropylene

Processing Method	Injection Molding
Attribute	Chemically Coupled
Forms	Pellets
Appearance	Black; Colors Available
Filler/Reinforcement	Glass Fiber, 15%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	6.0	g/10 min	ASTM D1238
Mechanical			
Tensile Strength at Yield	57.1	MPa	ASTM D638
Flexural Modulus	3160	MPa	ASTM D790
Tensile Elongation at Break	11	%	ASTM D638
Impact			
Notched Izod Impact	75	J/m	ASTM D256

Injection Parameters	Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	82 to 104	°C
Screw Speed	20 to 60	rpm
Processing (Melt) Temp	199 to 243	°C
Front Temperature	199 to 243	°C
Middle Temperature	199 to 243	°C
Rear Temperature	199 to 243	°C
Injection Rate	Moderate	
Back Pressure	<0.345	MPa
Mold Temperature	16 to 66	°C
Cushion	6.35 to 12.7	mm