

Technical Data Sheet

Polyfort FPP1A25CCBKBLK



Polypropylene, Unspecified (PP, Unspecified)

Product Description

FPP1A25CCBK is a 25% Glass-Reinforced, Chemically Coupled Polypropylene Homopolymer

Processing Method	Injection Molding
Attribute	Chemically Coupled
Forms	Pellets
Appearance	Black
Filler/Reinforcement	Glass Fiber, 25%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	6.0	g/10 min	ASTM D1238
Density - Specific Gravity	1.07	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield	68.9	MPa	ASTM D638
Flexural Modulus	4790	MPa	ASTM D790
Tensile Elongation at Break	10	%	ASTM D638
Impact			
Notched Izod Impact	80	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (66 psi)	157	°C	ASTM D648

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	82 to 104	°C
Screw Speed	20 to 60	rpm
Processing (Melt) Temp	199 to 243	°C
Front Temperature	199 to 243	°C
Middle Temperature	199 to 243	°C
Rear Temperature	199 to 243	°C
Injection Rate	Moderate	
Back Pressure	<0.345	MPa
Mold Temperature	16 to 66	°C
Cushion	6.35 to 12.7	mm