

Technical Data Sheet

Polyfort RPP20EC12BK-BK GAPEXBLK



Polypropylene, Unspecified (PP, Unspecified)

Product Description

Please contact A. Schulman for additional information.

Forms

Pellets

Application

Automotive Applications

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	71 to 82	°C
Nozzle Temperature	232 to 260	°C
Processing (Melt) Temp	221 to 238	°C
Front Temperature	232 to 260	°C
Middle Temperature	227 to 243	°C
Rear Temperature	221 to 238	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.138 to 0.345	MPa
Mold Temperature	38 to 66	°C
Cushion	5.08 to 12.7	mm