

Technical Data Sheet

Primefin E535/30GC

Polypropylene
LyondellBasell Industries
Engineering Plastics

Product Description

30% Glass Fiber Reinforced, Chemically Coupled, Impact Modified Polypropylene

Colors Available
Meets GMP.PP.003

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Impact Modifier
Features	• Chemically Coupled • Impact Modified
Appearance	• Colors Available

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.12	1.12 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	1.0 g/10 min	1.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	8500 psi	58.6 MPa	ASTM D638
Tensile Elongation (Break)	3.0 %	3.0 %	ASTM D638
Flexural Modulus	650000 psi	4480 MPa	ASTM D790
Flexural Strength	10000 psi	68.9 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 In (3.18 Mm))	3.0 ft·lb/in	160 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed	265 °F	129 °C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.