

Technical Data Sheet

Primefin V525HUV

Polypropylene
LyondellBasell Industries
Engineering Plastics

Product Description

UV Stabilized, Impact Modified Polypropylene

Colors Available
Meets GMP.PP.002

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Impact Modifier • UV Stabilizer
Features	• Impact Modified
Appearance	• Colors Available

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.910	0.908 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	3630 psi	25.0 MPa	ASTM D638
Tensile Elongation (Break)	> 10 %	> 10 %	ASTM D638
Flexural Modulus	135000 psi	931 MPa	ASTM D790
Flexural Strength	5500 psi	37.9 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 In (3.18 Mm))	2.2 ft·lb/in	120 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed	132 °F	55.6 °C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.