

Technical Data Sheet

Pro-fax EP494T



Polypropylene, Impact Copolymer

Product Description

Pro-fax EP494T polypropylene is available in pellet form. This resin is typically used in injection molding applications.

Regulatory Status

For regulatory compliance information, see *Pro-fax* EP494T [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Opaque Containers; Sports, Leisure & Toys
Market	Rigid Packaging
Processing Method	Injection Molding
Attribute	Contains Antistat; Low Temperature Impact Resistance

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	50	g/10 min	50	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm ³	0.90	g/cm ³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	170000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1170	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	3500	psi			ASTM D638
(50 mm/min)			24	MPa	ASTM D638
Tensile Elongation at Yield	5	%	5	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	1.7	ft-lb/in			ASTM D256
(23 °C, Method A)			91	J/m	ASTM D256
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	232	°F			ASTM D648
(0.45 MPa, Unannealed)			111	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.