

Technical Data Sheet

Pro-fax RP548N

Polypropylene, Random Copolymer

Product Description

Pro-fax RP548N nucleated polypropylene random copolymer is available in pellet form. This resin is typically used in injection molding applications and offers fast crystallization and antistatic properties.

Regulatory Status

For regulatory compliance information, see *Pro-fax* RP548N [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Caps & Closures; Containers
Market	Rigid Packaging
Processing Method	Injection Molding
Attribute	Contains Antistat; Good Dimensional Stability; Nucleated

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	11	g/10 min	11	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm ³	0.90	g/cm ³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	145000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1000	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	4000	psi			ASTM D638
(50 mm/min)			28	MPa	ASTM D638
Tensile Elongation at Yield	13	%	13	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	1.2	ft-lb/in			ASTM D256
(23 °C, Method A)			64	J/m	ASTM D256
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	180	°F			ASTM D648
(0.45 MPa, Unannealed)			82	°C	ASTM D648
Optical					
Haze, (45 mil)	40	%	40	%	ASTM D1003

Notes

These are typical property values not to be construed as specification limits.