

Technical Data Sheet

Pro-fax SG702



Polypropylene, Impact Copolymer

Product Description

Pro-fax SG702 high impact polypropylene copolymer is available in pellet form. This resin is typically used in injection molding applications and offers very good cold temperature impact resistance.

ASTM and ISO-based versions of the technical data sheet are available for *Pro-fax* SG702.

Regulatory Status

For regulatory compliance information, see *Pro-fax* SG702 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Automotive Parts; Containers; Sports, Leisure & Toys
Market	Automotive; Compounding; Consumer Products; Rigid Packaging
Processing Method	Compounding; Injection Molding
Attribute	Low Temperature Impact Resistance

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	18	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm ³	0.90	g/cm ³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	150000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1030	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	2900	psi			ASTM D638
(50 mm/min)			20	MPa	ASTM D638
Tensile Elongation at Yield	6	%	6	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	No Break				ASTM D256
(23 °C, Method A)			No Break		ASTM D256
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	180	°F			ASTM D648
(0.45 MPa, Unannealed)			82	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.

Automotive Specifications

- ▶ FCA MS-DB500 CPN 2073
- ▶ FCA MS-DB500 CPN 3047
- ▶ Ford ESB-M4D500-A
- ▶ Ford WSK-M4D604-A
- ▶ Ford WSS-M4D638-C
- ▶ Ford WSS-M4D638-D2
- ▶ GM GMP.PP.037
- ▶ GM GMP.PP.123
- ▶ GM GMW16008-T1
- ▶ GM GMW16208-T5