

## Technical Data Sheet

### *Pro-fax* SV258

Polypropylene, Impact Copolymer

#### Product Description

*Pro-fax* SV258 impact polypropylene copolymer is available in pellet form. This resin is typically used in extrusion applications and offers very good cold temperature impact resistance.

#### Regulatory Status

For regulatory compliance information, see *Pro-fax* SV258 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

|                          |                                                                                        |
|--------------------------|----------------------------------------------------------------------------------------|
| <b>Status</b>            | Commercial: Active                                                                     |
| <b>Availability</b>      | North America                                                                          |
| <b>Application</b>       | Automotive Parts; Corrugated Sheet; Opaque Containers                                  |
| <b>Market</b>            | Rigid Packaging                                                                        |
| <b>Processing Method</b> | Compounding; Extrusion Blow Molding; Sheet; Sheet and Profile Extrusion; Thermoforming |
| <b>Attribute</b>         | Good Dimensional Stability; Good Stiffness; Low Temperature Impact Resistance          |

| Typical Properties                    | Nominal Value | English Units     | Nominal Value | SI Units          | Test Method |
|---------------------------------------|---------------|-------------------|---------------|-------------------|-------------|
| <b>Physical</b>                       |               |                   |               |                   |             |
| Melt Flow Rate, (230 °C/2.16 kg)      | 1.2           | g/10 min          | 1.2           | g/10 min          | ASTM D1238  |
| Density, (23 °C)                      | 0.90          | g/cm <sup>3</sup> | 0.90          | g/cm <sup>3</sup> | ASTM D792   |
| <b>Mechanical</b>                     |               |                   |               |                   |             |
| Flexural Modulus                      |               |                   |               |                   |             |
| (0.05 in/min, 1% Secant, Procedure A) | 180000        | psi               |               |                   | ASTM D790   |
| (1.3 mm/min, 1% Secant, Procedure A)  |               |                   | 1240          | MPa               | ASTM D790   |
| Tensile Strength at Yield             |               |                   |               |                   |             |
| (2 in/min)                            | 4100          | psi               |               |                   | ASTM D638   |
| (50 mm/min)                           |               |                   | 28            | MPa               | ASTM D638   |
| Tensile Elongation at Yield           | 11            | %                 | 11            | %                 | ASTM D638   |
| <b>Impact</b>                         |               |                   |               |                   |             |
| Notched Izod Impact Strength          |               |                   |               |                   |             |
| (73 °F, Method A)                     | 3.9           | ft-lb/in          |               |                   | ASTM D256   |
| (23 °C, Method A)                     |               |                   | 208           | J/m               | ASTM D256   |
| <b>Thermal</b>                        |               |                   |               |                   |             |
| Deflection Temperature Under Load     |               |                   |               |                   |             |
| (66 psi, Unannealed)                  | 180           | °F                |               |                   | ASTM D648   |
| (0.45 MPa, Unannealed)                |               |                   | 82            | °C                | ASTM D648   |

#### Notes

These are typical property values not to be construed as specification limits.