

## Technical Data Sheet

### Purell RP271G



Polypropylene, Random Copolymer

#### Product Description

Purell RP271G is a low melt flow polypropylene random copolymer resin with good clarity, good impact properties, high temperature resistance suitable for autoclave sterilization. Typical customer application are medical IV solution bottles made by extrusion blow molding process.

#### Regulatory Status

For regulatory compliance information, see Purell RP271G [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand
Application	Bottles For Consumer Goods; Healthcare Applications
Market	Healthcare
Processing Method	Extrusion Blow Molding
Attribute	High Clarity; Random Copolymer

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	1.7	g/10 min	ASTM D1238
Density	0.90	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>			
Flexural Modulus	900	MPa	ASTM D790
Tensile Strength at Yield	26	MPa	ASTM D638
Tensile Elongation at Yield	14	%	ASTM D638
<b>Impact</b>			
Notched Izod Impact Strength, (23 °C)	80	J/m	ASTM D256
<b>Thermal</b>			
Deflection Temperature Under Load, (0.46 N/mm <sup>2</sup> )	88	°C	ASTM D648

#### Notes

These are typical property values not to be construed as specification limits.