(+) 188 1699 6168 hongrunplastics.com

## **Technical Data Sheet**

## Pro-fax RP223L

Polypropylene, Random Copolymer

## LYB LyondellBasell

## **Product Description**

*Pro-fax* RP223L is a medium melt flow rate polypropylene random copolymer available in pellet form. This resin is typically used in cast and oriented film applications. In film applications it offers exceptional clarity, gloss, improved cold temperature impact resistance and lower and broader heat sealing properties as compared to conventional polypropylene homopolymer. *Pro-fax* RP223L is a barefoot resin with no slip, anti-block or other property specific additives. This product is manufactured with a non-phthalate catalyst system and is produced without animal derived components.

Application Bags & Pouches; Breathable Film; Film Wrap; Food Packaging Film; Heavy Duty

Packaging; Hygiene Film; Stationery Film; Twist Wrap Film

Processing Method Cast Film; Oriented Film

Attribute Good Heat Seal; Good Optical Properties; Good Processability; Medium Flow

	Nominal	English	Nominal	SI	
Typical Properties	Value	Units	Value	Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	7.0	g/10 min	7.0	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm³	0.90	g/cm³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	130000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			896	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	3800	psi			ASTM D638
(50 mm/min)			26.2	MPa	ASTM D638
Tensile Elongation at Yield	13	%	13	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	0.95	ft-lb/in			ASTM D256
(23 °C, Method A)			51	J/m	ASTM D256
Gardner Impact, (23 °C, Geometry GC)	160	in-lbs	18	J	ASTM D5420
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	174	°F			ASTM D648
(0.45 MPa, Unannealed)			79	°C	ASTM D648