

## Technical Data Sheet

### *Pro-fax* RP913J



Polypropylene, Random Copolymer

#### Product Description

*Pro-fax* RP913J clarified random copolymer polypropylene is available in pellet form. This resin is typically used in sheet extrusion/thermoforming and other rigid packaging applications.

|                   |                              |
|-------------------|------------------------------|
| Application       | Clear Containers             |
| Market            | Rigid Packaging              |
| Processing Method | Thermoforming                |
| Attribute         | High Clarity; High Stiffness |

| Typical Properties                    | Nominal Value | English Units     | Nominal Value | SI Units          | Test Method |
|---------------------------------------|---------------|-------------------|---------------|-------------------|-------------|
| <b>Physical</b>                       |               |                   |               |                   |             |
| Melt Flow Rate, (230 °C/2.16 kg)      | 3.5           | g/10 min          | 3.5           | g/10 min          | ASTM D1238  |
| Density, (23 °C)                      | 0.90          | g/cm <sup>3</sup> | 0.90          | g/cm <sup>3</sup> | ASTM D792   |
| <b>Mechanical</b>                     |               |                   |               |                   |             |
| Flexural Modulus                      |               |                   |               |                   |             |
| (0.05 in/min, 1% Secant, Procedure A) | 230000        | psi               |               |                   | ASTM D790   |
| (1.3 mm/min, 1% Secant, Procedure A)  |               |                   | 1590          | MPa               | ASTM D790   |
| Tensile Strength at Yield             |               |                   |               |                   |             |
| (2 in/min)                            | 5300          | psi               |               |                   | ASTM D638   |
| (50 mm/min)                           |               |                   | 37            | MPa               | ASTM D638   |
| Tensile Elongation at Yield           | 10            | %                 | 10            | %                 | ASTM D638   |
| <b>Impact</b>                         |               |                   |               |                   |             |
| Notched Izod Impact Strength          |               |                   |               |                   |             |
| (73 °F, Method A)                     | 1.1           | ft-lb/in          |               |                   | ASTM D256   |
| (23 °C, Method A)                     |               |                   | 59            | J/m               | ASTM D256   |
| <b>Thermal</b>                        |               |                   |               |                   |             |
| Deflection Temperature Under Load     |               |                   |               |                   |             |
| (66 psi, Unannealed)                  | 228           | °F                |               |                   | ASTM D648   |
| (0.45 MPa, Unannealed)                |               |                   | 109           | °C                | ASTM D648   |
| <b>Optical</b>                        |               |                   |               |                   |             |
| Haze, (45 mil)                        | 23            | %                 | 23            | %                 | ASTM D1003  |