(+) 188 1699 6168 hongrunplastics.com

## **Technical Data Sheet**

## Sequel 1440 FP GREY AC2

Polypropylene Compounds

## LYB LyondellBasell

## **Product Description**

*Sequel* 1440 FP GREY AC2 engineered polyolefin material is typically used for large automotive exterior applications that require very good impact properties at low temperatures, excellent paintability, and processability.

**Application** Exterior Automotive Applications

Market Automotive

Processing Method Injection Molding

Attribute Good Impact Resistance; Good Moldability; High Flow; Low Temperature Impact

Resistance; Paintable

	Nominal		Test Method
Typical Properties	Value	Units	
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.96	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C)	1250	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	22	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (-40 °C)	4.8	kJ/m²	ISO 180
Additional Information			
Mold Shrinkage			ISO 294-4

Please contact LyondellBasell for shrinkage recommendations.