



Sequel 1440HF-PUV

Compounded Polyolefin

Product Description

Sequel 1440HF-PUV engineered polyolefin material is designed for large automotive exterior applications that require ductile impact properties at low temperatures, excellent paintability, and processability.

Product Characteristics

Status	Commercial: Restricted
Test Method used	ISO
Availability	North America
Processing Methods	Injection Molding
Features	Ductile, Paintable, Good Processability
Typical Customer Applications	Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.94	g/cm ³
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	27	g/10 min
Mechanical			
Flexural modulus	ISO 178	1200	MPa
<i>Note: 80x10x4mm specimen</i>			
Additional Information			
Mold shrinkage	ISO 294-4		
<i>Note: Please contact LyondellBasell for shrinkage recommendations.</i>			

Notes

Typical properties; not to be construed as specifications.