

## Technical Data Sheet

### *Sequel* 1588-UV GXH Black



Polypropylene Compounds

#### Product Description

*Sequel* 1588-UV GXH Black thermoplastic polyolefin material exhibits significantly greater mar resistance than conventional TPOs that typically is used for automotive applications that demand low warpage, low CLTE, and has excellent scratch and mar resistance.

Application	Automotive Parts; Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	UV Stabilized

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	18.1	g/10 min	ISO 1133-1
Density, (23 °C)	1.03	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus, (23 °C, 2 mm/min)	1785	MPa	ISO 178
Tensile Stress at Yield, (23 °C, 50 mm/min)	20.4	MPa	ISO 527-1, -2
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			