



Sequel 2380

Compounded Polyolefin

Product Description

Sequel 2380 thermoplastic polyolefin material is designed for large automotive interior applications that require stiffness and good dimensional stability over a broad temperature range. This material exhibits excellent processability and appearance.

Product Characteristics

Test Method used	ISO
Processing Methods	Injection Molding
Features	Good Dimensional Stability, Good Processability, High Stiffness
Typical Customer Applications	Instrument Panels, Interior Applications

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	1.04	g/cm ³
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	22	g/10 min
Mechanical			
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	24.0	MPa
Note: 150x10x4 mm specimen			
Flexural modulus (2 mm/min)	ISO 178	2000	MPa
Note: 80x10x4mm specimen			
Impact			
Multiaxial Impact Strength (23 °C, 2.2 m/s)	ASTM D3763	23	J
Additional Information			
Mold shrinkage	ISO 294-4		