(+) 188 1699 6168 hongrunplastics.com



Softell DKG100N

Compounded Polyolefin

Product Description

Softell DKG100N is a 10% glass filled, thermoplastic polyolefin elastomer compound for injection molding. The grade has been designed primarily for automotive interior applications that require low gloss, soft touch, high rigidity, good impact and scratch and mar resistance.

Product Characteristics

Test Method used ISO

Processing Methods Injection Molding

Features Ductile, Low Gloss, Good Impact Resistance , Scratch

Resistant, Soft

Typical Customer Applications Interior Applications

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	20	g/10 min
Density (23°C)	ISO 1183	0.96	g/cm³
Mechanical			
Tensile Stress at Yield (23°C)	ISO 527-1, -2	28	MPa
Tensile Strain at Yield (23°C)	ISO 527-1, -2	10	%
Flexural modulus (23°C)	ISO 178	1750	MPa
Impact			
Notched izod impact strength	ISO 180		
(23°C)		30	kJ/m²
(-30°C)		10	kJ/m²
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	140	°C
Additional Information			
Mold shrinkage	ISO 294-4		