

## Technical Data Sheet

### Softell TKG 2148P C12958



Polypropylene Compounds

#### Product Description

*Softell* TKG 2148P C12958 is a 20% glass fiber reinforced PP copolymer with very high UV resistance, good soft touch haptics, high flowability, high dimensional stability and very high scratch resistance. Due to pigmentation, ash content may vary between 20 -25 %. Material shows low shrinkage and has a very low warpage tendency. This grade is delivered in C12958 color version. This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

Application	Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Good UV Resistance; High Stiffness; Low Shrinkage

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C)	1.06	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	2850	MPa	ISO 178/A1
Tensile Modulus, (23 °C)	2550	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C)	12	%	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	30	kJ/m <sup>2</sup>	ISO 179-1/1eA
(-30 °C)	9	kJ/m <sup>2</sup>	ISO 179-1/1eA
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	142	°C	ISO 75B-1, -2