

## Technical Data Sheet

### Softell TKG 300N G82732



Polypropylene Compounds

#### Product Description

Softell TKG 300N is a 25% glass fiber reinforced PP copolymer, offering low gloss & excellent surface appearance combined with high scratch resistance. The grade exhibits soft touch haptics and very good dimensional stability.

The product reflects the latest advancements in resin synthesis and compounding technology.

This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

Application	Automotive Parts; Instrument Panels; Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Excellent Processability; Excellent Stiffness; Good Abrasion Resistance; Good Color Stability; Good Dimensional Stability; Good Surface Finish; High Impact Resistance; High Toughness; Low Gloss; Low Shrinkage; Low to No Odor; Low VOC Emission; Low Warpage; Noise Damping; Pleasing Surface Appearance; Scratch Resistant; Soft; Weldable

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	6	g/10 min	ISO 1133-1
Density, (23 °C)	1.09	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	2300	MPa	ISO 178/A1
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	30	kJ/m <sup>2</sup>	ISO 179-1/1eA
(0 °C)	20	kJ/m <sup>2</sup>	ISO 179-1/1eA
(-30 °C)	8	kJ/m <sup>2</sup>	ISO 179-1/1eA
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	125	°C	ISO 75B-1, -2