

## Technical Data Sheet

### Softell TKS 209N NAT



Polypropylene Compounds

#### Product Description

Softell TKS 209N NAT is an unfilled PP copolymer, with very low rigidity, good scratch resistance and very low gloss. Product is also available as a customized color matched, pellet form. This grade is delivered in natural color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

Application	Automotive Parts; Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Low Gloss; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	6	g/10 min	ISO 1133-1
Density, (23 °C)	0.92	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	115	MPa	ISO 178/A1
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	No Break		ISO 179-1/1eA
(-30 °C)	100	kJ/m <sup>2</sup>	ISO 179-1/1eA