

Technical Data Sheet

QR Resin QR-4004


Polyphenylene Ether + PA 66
Engineering Plastics

General			
Material Status	• Commercial: Active		
Availability	• North America		
Features	• Chemical Resistant	• Paintable	
Appearance	• Black		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.08	1.08 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (280°C/2.16 kg)	4.0 g/10 min	4.0 g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in (3.18 mm))	0.010 in/in	1.0 %	ASTM D955
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	8000 psi	55.2 MPa	ASTM D638
Flexural Modulus	300000 psi	2070 MPa	ASTM D790
Flexural Strength (Yield)	12500 psi	86.2 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	3.5 ft·lb/in	190 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	290 °F	143 °C	
264 psi (1.8 MPa), Unannealed	255 °F	124 °C	

Technical Data Sheet

QR Resin QR-4004

Polyphenylene Ether + PA 66
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	200 to 225 °F	93 to 107 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Drying Time, Maximum	6.0 hr	6.0 hr
Suggested Max Moisture	0.02 %	0.02 %
Rear Temperature	480 to 530 °F	249 to 277 °C
Middle Temperature	490 to 540 °F	254 to 282 °C
Front Temperature	500 to 550 °F	260 to 288 °C
Nozzle Temperature	520 to 560 °F	271 to 293 °C
Processing (Melt) Temp	510 to 550 °F	266 to 288 °C
Mold Temperature	150 to 200 °F	66 to 93 °C

Notes

These are typical property values not to be construed as specification limits.