

Technical Data

www.aschulman.com



AQUALOY® 282

Glass Fiber Reinforced, Surface Modified, Modified PPE Blend

Properties	Standard	Parameters	Unit
Chemical			
Moisture (Water Content)		0.04 - 0.10	%
Water Absorption	ASTM D570	24 hrs.	0.025 %
General			
Specific Gravity	ASTM D792	1.47	g/cm ³
Mechanical			
Flexural Modulus	ASTM D790	1.3mm/min, 50 mm span	976.8 kPSi
Flexural Strength	ASTM D790	@ 1.3 mm/min, 50 mm span	1.46 kPSi
Izod Impact Strength, Notched	ASTM D256		.594 ft-lbs/in
Tensile Elongation	ASTM D638	@ break 5mm/min	1.8 MPa
Tensile Strength @ Break	ASTM D638	5 mm/min	58 MPa
Processing			
Melt Temperature		240-270	°C
Mold Shrinkage	ASTM D955	.24	%
Mold Temperature		90-110	°C
Predrying		2-4 hours @ 100	°C
Thermal			
CLTE	ASTM D696	-30 to 100°C cross flow	48.5x10 ⁻⁶ mm/mm/°C
CLTE	ASTM D696	-30 to 100°C flow	25.4 x 10 ⁻⁶ mm/mm/°C
Heat Deflection Temperature	ASTM D648	@ 1.82 MPa, 264 psi	279.8 °F

Reported values pertain only to natural resins: pigmenting may vary properties. Pellet cut, size, color, and other properties may vary depending on the manufacturing location.

NOTE: While the information herein is believed to be reliable and correct, nothing herein is intended and should not be construed as a representation of warranty, expressed or implied as to results obtained or to be obtained by others who may make use of this information or with respect to the absence, existence or validity of patent rights, if any of others involving any composition or process herein referred to; or an inducement or recommendation for the violation of any such patent rights; and responsibility therefore is disclaimed.