

Technical Data Sheet

Bmc 1000

Thermoset Polyester
LyondellBasell Industries
Engineering Plastics

General		
Filler / Reinforcement	• Glass Fiber	
Uses	• Household Goods • Microwave Cookware	
Agency Ratings	• FDA	
Appearance	• Colors Available	
Forms	• Pellets	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.85	1.84 g/cm ³	ASTM D792
Water Absorption (24 Hr)	0.070 %	0.070 %	ASTM D570
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	6000 psi	41.4 MPa	ASTM D638
Flexural Modulus	1.00E+6 psi	6890 MPa	ASTM D790
Flexural Strength (Yield)	16000 psi	110 MPa	ASTM D790
Compressive Strength	16000 psi	110 MPa	ASTM D695
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	3.0 ft·lb/in	160 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Barcol Hardness	30	30	ASTM D2583
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed	400 °F	204 °C	ASTM D648
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Dielectric Strength	410 V/mil	16 kV/mm	ASTM D149
Arc Resistance (0.0625 In (1.59 Mm))	180 sec	180 sec	ASTM D495
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.6 Mm))	HB	HB	UL 94

Notes

These are typical property values not to be construed as specification limits.