

Technical Data Sheet

Bmc 5209-12940

Thermoset Polyester
LyondellBasell Industries
Engineering Plastics

Product Description

BMC 5209-12940 molding compound is a mineral filled, glass fiber-reinforced polyester compound suitable for compression, transfer and stuffer injection molding. It is a high impact material produced in bulk form for maximum strength. Other characteristics are good over all electrical properties and flame resistance. Typical applications include circuit breaker housings, standoff insulators, bus supports and tool housings. BMC 5209-12940 molding compound can be produced in a range on industrial colors.

General


Filler / Reinforcement	• Glass\Mineral		
Features	• Flame Retardant	• Good Electrical Properties	• High Impact Resistance
Uses	• Electrical Housing	• Electrical/Electronic Applications	
Appearance	• Colors Available		
Forms	• BMC - Bulk Molding Compound		
Processing Method	• Compression Molding	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.89	1.89 g/cm ³	ASTM D792
Water Absorption (24 Hr, 73°F (23°C))	0.080 %	0.080 %	ASTM D570
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, Compression Molded)	8500 psi	58.6 MPa	ASTM D638
Flexural Strength (Compression Molded)	24000 psi	165 MPa	ASTM D790
Compressive Strength	26000 psi	179 MPa	ASTM D695
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (Compression Molded)	8.0 ft·lb/in	430 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Barcol Hardness	44	44	ASTM D2583
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Unannealed, Compression Molded	500 °F	260 °C	
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Dielectric Strength (Method A (short-time))	400 V/mil	16 kV/mm	ASTM D149
Arc Resistance	180 sec	180 sec	ASTM D495
Comparative Tracking Index (CTI)	600 V	600 V	UL 746A
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.06 In (1.6 Mm)	V-0	V-0	
0.13 In (3.2 Mm)	• V-0	• V-0	
0.25 In (6.4 Mm)	• 5V	• 5V	
	V-0	V-0	

Technical Data Sheet

Bmc 5209-12940

Thermoset Polyester
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Mold Temperature	280 to 330 °F	138 to 166 °C

Notes

These are typical property values not to be construed as specification limits.