

Technical Data Sheet

Bmc T70-7002(I25)

Thermoset Polyester
LyondellBasell Industries
Engineering Plastics

General			
Uses	• Automotive Applications	• Housings	
Automotive Specifications	• GM GMP.UP.014		
Appearance	• Black		
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.95	1.95 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	11100 psi	76.6 MPa	ASTM D638
Flexural Modulus	2.10E+6 psi	14500 MPa	ASTM D790
Flexural Strength (Yield)	23600 psi	163 MPa	ASTM D790
Compressive Strength	25800 psi	178 MPa	ASTM D695
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Unnotched Izod Impact	6.5 ft·lb/in	350 J/m	ASTM D4812
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Barcol Hardness	53	53	ASTM D2583
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Dielectric Strength	380 V/mil	15 kV/mm	ASTM D149
Arc Resistance	181 sec	181 sec	ASTM D495
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.06 In (1.5 Mm)	HB	HB	
0.09 In (2.2 Mm)	HB	HB	
0.12 In (3.1 Mm)	HB	HB	

Additional Information			
Barcol Hardness, ASTM D2583: 50 to 55			
UL Flame Rating, UL 94, 0.058 to 0.062 in: HB			
UL Flame Rating, UL 94, 0.075 to 0.1 in: HB			
UL Flame Rating, UL 94, 0.120 to 0.125 in: HB			

Notes

¹ Type I

Notes

These are typical property values not to be construed as specification limits.